

Technical data sheet for hardened and tempered spring steel wire

VG 08 - HD/2019-02 Revision A

Scope

This technical data sheet covers hardened and tempered spring steel wires in **SiCrV alloyed** steel grades with **extra high tensile** strengths.

Inspection of the wire surface

The complete length of the wire will be checked by an eddy current check during the drawing process

Chemical composition (heat analysis)

	C %	Si %	Mn %	P %	S %	Cu %	Cr %	V %
min.	0,54	1,35	0,35				0,50	0,10
max.	0,65	1,60	0,65	0,020	0,020	0,12	0,70	0,25

Mechanical properties

Dia. of wire			Tensile strength		Min. reduction of area
d mm	Tolerance mm		Rm MPa		Z %
>	≤	±	min.	max.	-
2,50	3,00	0,025	2.100	2.230	45
3,00	4,00		2.050	2.200	
4,00	6,00	0,030	2.030	2.180	
6,00	9,00	0,035	2.030	2.180	
9,00	15,00	0,040	2.000	2.150	
15,00	18,50	0,050	1.950	2.100	35
The out of roundness shall not be more than 50% of the total diameter tolerance.			The tensile strength within one coil can scatter by max. 50 MPa, within one delivery by max. 70 MPa.		

Physical properties

Modulus of elasticity	E [GPa]	206
Shear modulus	τ [GPa]	79,5
Yield strength 0,2%	$R_{p0,2}$	min. 0,9 x tensile strength of the wire

Surface finish

Permissible depth of surface defects	max. 60 μm eddy current checked
Partial decarburization	max. 0,5 % of the wire- \emptyset

Heat treatment - recommended values for tempering temperature

After coiling the springs	$\approx 400^{\circ}\text{C}$, 30 min.
After shot peening the springs	$\approx 250^{\circ}\text{C}$, 30 min.